

# Medite® FR

## MDF

MEDFORD, OR

TECHNICAL DATA	IMPERIAL	METRIC
<b>Widths</b>	4 & 5 ft	1.22 & 1.52 m
<b>Lengths</b>	up to 18 ft	up to 5.49 m
<b>Thicknesses</b>	1/4 – 1-1/2 in	6.35 – 38.1 mm
<b>Density</b>	50 lbs/ft <sup>3</sup>	801 kg/m <sup>3</sup>
<b>Internal Bond</b>	200 psi	1.38 N/mm <sup>2</sup>
<b>Modulus of Rupture/MOR</b>	4,000 psi	27.6 N/mm <sup>2</sup>
<b>Modulus of Elasticity/MOE</b>	500,000 psi	3,447 N/mm <sup>2</sup>
<b>Hardness/MOH</b>	1,200 lbs	5,338 N
<b>Screw Holding – Face</b>	300 lbs	1,334 N
<b>Screw Holding – Edge</b>	250 lbs	1,112 N
<b>Thickness Swell</b>	7.0%	
<b>Linear Expansion</b>	0.30%	
<b>Moisture Content</b>	6 - 9%	
<b>Flame Spread Rating</b>	Class A (1)	
<b>Dimensional Tolerances:</b>		
Length/Width	±0.080 in	±2.0 mm
Squareness	±0.036 in/ft	±3.0 mm/m
Thickness – panel average from specified	±0.005 in	±0.125 mm
Thickness – variance from panel average	±0.005 in	±0.125 mm

Values represent averages for 3/4" thick panels. Mechanical properties are tested in accordance with ASTM D1037.

Customer-specified grades are available by request and subject to minimum order quantities.

## MEDIUM DENSITY FIBERBOARD

MDF panels with certified class A (1) flame spread rating made with no added formaldehyde (NAF).

## COMMON APPLICATIONS

- Elevator wall panels
- Casework and furniture (Class 1 required)
- Airport jetways
- Shopping mall kiosks
- Decorative profiled wall panels

# Medite® FR

MDF

MEDFORD, OR

## STANDARDS & CERTIFICATIONS

Roseburg Medite FR MDF is tested and certified to meet or exceed the following standards and certifications.

### ANSI A208.2 - American National Standard – Medium Density Fiberboard (MDF) for Interior Applications

- ✓ Meets or exceeds ANSI A208.2 Grade 130

### Formaldehyde Emissions Regulations – Third party certified (TPC-1) to meet the requirements of:

- ✓ EPA Formaldehyde Emission Regulation, TSCA Title VI\*
- ✓ Standards Council of Canada Formaldehyde Emissions Standard for Composite Wood Products – CAN/CSA 0160-16\*
- ✓ No Added Formaldehyde (NAF) Exempt - State of CA Executive Order N-20-313\*

### No Added Formaldehyde

- ✓ No Added Formaldehyde (NAF) Exempt - State of CA Executive Order N-20-313\*

### Recycled Content

- ✓ Scientific Certification Systems Certified 82% pre-consumer recycled content (SCS-MC-01093)\*

### Environmental Product Declaration

- ✓ Type III Product Specific EPD Certified by UL Environment




### Forest Stewardship Council®

- ✓ Scientific Certification Systems Certified (SCS-COC/CW-00300) – FSC-C017580 FSC® Mix and FSC® Controlled Wood - AVAILABLE OPTION\*

### ASTM E84 – Standard test method for surface burning characteristics of building materials

- ✓ Guardian Fire Testing Laboratories Certified Class A Rating

ASTM E84 (GL-67515)  
 CAN/ULC S102 (GL-49215)  
 ASTM E2768 (GL-6-2-17-Y)\*

 <small>www.firetesting.com</small> <b>GL 67515</b> <b>Medite FR</b> <small>Mineral and Fiber Boards        Surface Burning        Characteristics</small> <small>Tested to: ASTM E84-14        1/4 in. - 1-1/2in.</small> <small>Flame Spread 15        Smoke Developed 5</small>	 <small>www.firetesting.com</small> <b>GL 49215</b> <b>Medite FR</b> <small>Mineral and Fiber Boards        Surface Burning        Characteristics</small> <small>Tested to: CAN/ULC-S102-10        1/2 in. - 1-1/2in.</small> <small>Flame Spread 10        Smoke Developed 5</small>	 <small>www.firetesting.com</small> <b>GL-6-2-17-Y</b> <b>Medite FR</b> <small>Mineral and Fiber Boards        Extended Duration Surface        Burning Characteristics</small> <small>Tested to: ASTM E2768-11        3/8 in. - 1-1/2in.</small> <small>MEETS CONDITIONS OF        CLASSIFICATION</small>
---	---	---

### Eco-Certified Composite Grademark Program

- ✓ CPA ECC Sustainability Standard\*

\*Certificates and documentation available at [Roseburg.com](http://Roseburg.com)

## GREEN BUILDING SUPPORT:

For LEED® and other green building support documentation, visit [roseburg.com/product/medite-fr](http://roseburg.com/product/medite-fr)



3660 Gateway St, Springfield, OR 97477  
 800.245.1115 | [roseburg.com](http://roseburg.com)



MEDITE 3D MEDFORD 08282020