# 42# PREMIUM COMMERCIAL



WOODGRAIN 42# COMMERCIAL PARTICLEBOARD PROVIDES MANUFACTURING AND SHIPPING ECONOMIES THAT TRANSLATE INTO LOWER PURCHASE COSTS. LIGHT WITHOUT SACRIFICE. ENGINEERED FOR INTERIOR USE ONLY.

### **DESCRIPTION**

An engineered composite panel wood product made from 100% recycled Ponderosa pine and associated species of western wood particles formed and bonded with an interior resin.

# SPECIFICATION CONFORMANCE

Physical and Mechanical Properties are averages of all thicknesses from normal product runs.

### THICKNESS RANGE

1/2" through 1" or 12 mm through 25 mm

## WOODGRAIN PARTICLEBOARD COMPLIES WITH:

EPA TSCA Title VI, HUD 24 CFR 3280, CCR 93120 CARB ATCM Phase 2, CAN/CSA-0160-16 (Formaldehyde Emissions) ECC CPA 4-11 (Sustainability); ANSI A208.1 2016 (Physical Properties)

Flame spread rating is class C (International Code Council – International Fire Code® and National Fire Protection Association 101 Life Safety Code®) as tested to ASTM E84 and CAN/ULC-S102-10.

| MANUFACTURING STANDARDS: AVERAGE        | IMPERIAL    | METRIC                   |
|---|-------------|--------------------------|
| Density                                 | 42.0 lb/ft³ | 0.673 g/cm <sup>3</sup>  |
| Internal Bond                           | 85 psi      | 0.586 N/ mm <sup>2</sup> |
| Screw Hold - Face                       | 200 lbs     | 889.6 N                  |
| Screw Hold - Edge                       | 157 lbs     | 698.37 N                 |
| Formaldehyde, Emissions (TSCA Title VI) | < 0.09 ppm  | < 0.09 ppm               |
| Linear Expansion - Maximum              | 0.35%       | 0.35%                    |
| Water Absorption - Maximum              | 20%         | 20%                      |
| Moisture Content                        | 7%          | 7%                       |
| Sanding                                 | 120 grit    | -                        |

| MANUFACTURING TOLERANCES                                      | IMPERIAL    | METRIC      |
|---|-------------|-------------|
| Thickness Average from Target Value*                          | ± 0.005 in  | ± 0.127 mm  |
| Thickness Range (within panel) from Panel Average Value       | ± 0.004 in  | ± 0.1016 mm |
| Length and Width (within panel) from Specified Size           | ± 0.0625 in | ± 1.5875 mm |
| Squareness (within panel) Maximum Deviation Between Diagonals | 0.125 in    | 3.175 mm    |
| Straightness (within panel) Maximum bow per 8' Length         | 0.0625 in   | 1.5875 mm   |

<sup>\*</sup>Target value 0.005 under nominal

For more information, including sales terms and conditions:

Visit our website: Woodgrain.com

 $Send\ us\ an\ Email:\ Particle board Sales@Woodgrain.com$ 

Give us a Call: 888-264-7372



